


TECHNICAL NOTES

NOTES	CONTENT
GENERAL NOTES	
Wood treatment	<ul style="list-style-type: none"> - The wood must be treated with pesticides and kiln-dried to ensure adequate humidity. - Wood sealer should be applied for later use. - Apply wood preservative on all surfaces. - Painting the outside of the bottom with bitumastic paint. - All joints should be treated with an asphalt-based or bitumastic compound during the construction. It may be necessary to caulk eventual bad leaks with caulking compound afterwards. - All wood pieces must be glued together with white glue before nailing.

PROJECT Flat Bottom Boat Scow-Type	CREATED BY J. Zeron	APPROVED BY A. Morillo	DATE 08/10/2021	VERSION 1.0
PART NAME Technical notes	FILE NAME			POS C1
PUBLISHED BY OHO e.V.		DOC. TYPE Technical notes	MATERIAL	QUANTITY
LICENCE CC-BY-SA 4.0		SCALE	SHEET 5 /17	